

SPECIFICATION DATA SHEET

FaraHyol M (1.000-1.600) KDa

EU INCI name	US INCI name	CAS n.	EC n.
Sodium Hyaluronate	Sodium Hyaluronate	9067-32-7	(polymer)

ANALYTICAL SPECIFICATION						
Parameter	Unit	Requirement	Method			
PHYSICAL-CHEMICAL						
Aspect	-	Powder	Comparison with the standard			
Color	-	White	Comparison with the standard			
Odor	-	Characteristic	Comparison with the standard			
Molecular weight	kDa	1.000-1.600	Calculated			
Intrinsic Viscosity	dL/g	19-26	S.H. Ph.Eur.Monograph			
pH (0.1%sol)	i.u.	6,0 – 8,0	Ph.Eur.2.2.3			
Transparency	T550nm	≥ 99%	Ph.Eur.2.2.25			
Loss on drying	%	≤ 10.0	Ph.Eur.2.2.32			
Protein	%	≤ 0.1	S.H. Ph.Eur.Monograph			
Ashes	%	≤13	S.H. Ph.Eur.Monograph			
Sodium Hyaluronate assay	%	≥ 95	S.H. Ph.Eur.Monograph			
Glucuronic acid assay	%	≥ 46	S.H. Ph.Eur.Monograph			
MICROBIOLOGICAL						
Total bacterial count	CFU/g	≤ 100	Ph.Eur.2.6.12			
Total yeast and mould count	CFU/g	≤100	Ph.Eur.2.6.12			



Staphylococcus aureus	/g	Negative	Ph.Eur.2.6.13			
Pseudomonas Aeruginosa	/g	Negative	Ph.Eur.2.6.13			
Escherichia coli	/g	Negative	Ph.Eur.2.6.13			
Candida Albicans	/g	Negative	Ph.Eur.2.6.13			
OTHER DATA NOT SUBJECTED TO ANALYTICAL CERTIFICATION						
Parameter	Unit	Typical result				
Heavy Metal	ppm	<u>≤ 10</u>				
Arsenic	ppm	<u>≤ 0.5</u>				
Lead	ppm	≤ 1.0				
Mercury	ppm	≤ 0.1				
Cadmium	ppm	≤ 0.3				
Iron	ppm	≤80				
Chlorides	%	≤0,5				

<u>Storage</u>: keep the product in the original container well closed in fresh and dry place, repaired from humidity, light or heat sources. Temperature at 2-10°C cool and dry place

Period of best use: 24 months from production date, in sealed original container, if stored as described above.

THE INFORMATION CONTAINED IN THIS DOCUMENT ARE BASED ON OUR CURRENT SCIENTIFIC KNOWLEDGE AND DOES NOT DISCHARGE THE USER FROM THE CONTROL OF THE PRODUCT BEFORE THE USE. THE INFORMATION ARE CAREFUL AND RELIABLE BUT IT SHOULD NOT BE TAKEN AS EXPRESSING OR IMPLYING ANY WARRANTY CONCERNING THE PRODUCT CHARACTERISTICS. THE USER, UNDER HIS OWN RESPONSIBILITY, MUST RESPECT THE RULES AND LAWS IN FORCE. ROELMI ASIA-PACIFIC Ltd DOES NOT TAKE LIABILITY FOR ANY DAMAGE TO PEOPLE OR PROPERTY FOR IMPROPER USE AND DECLINES ANY RESPONSABILITY IN CASE THE USE OF THE PRODUCT INFORMATION MIGHT TAKE TO PATENT INFRINGEMENT OF THIRD PARTIES.

THE PRESENT DOCUMENT SUBSTITUTES AND CANCELS THE PREVIOUS VERSION.